



TEST CERTIFICATE

Date Received 11 January 2012
Date Issued 07 February 2012
Client Kartallar Boya
Kosklucesme Mahallesi
Yeni Bagdat Caddesi
No: 136 Gebze
Kocaeli
Turkey

PRA Reference 75221-137

Samples Submitted Karpox Armora ZP + Karpoly Pyramidal
Karpox Armora ZP + Karacryl Duralack


Work Requested 500 hour QUV weathering to
ASTM D4587

Results

Sample	Colour Change (Delta E)
Karpox Armora ZP + Karpoly Pyramidal	0.499
Karpox Armora ZP + Karacryl Duralack	0.358

A delta E value of 1 is generally accepted as being noticeable to the average observer

Signed.....
Jon Gadd

Approved.....
Tessa Glazier
Head of Testing Services