

KARDEN UNIMARINE

PRODUCT CODE: KBK 020112

GENERAL PURPOSE MARINE PRIMER-SURFACE TOLERANT

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Anticorrosive, Universal Epoxy Primer
DESCRIPTION, AREAS OF USE	Karden Unimarine is a two component, polyamide cured general purpose and surface tolerant epoxy primer for marine industry. It has excellent adhesion, chemical resistance, underwater resistance and high-build properties. Could also be used as intermediate or topcoat at multilayer heavy duty applications. Recoatability, flexibility and cure-ability are improved. Has outstanding in can and application stability. Provides even better results than coal-tar epoxies. Suitable for impressed current systems.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 - 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) - +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Redbrown, Gray, Black, White
APPEARANCE	Semi Matt (ASTM D 523)
SPECIFIC GRAVITY	1.35±05 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	%60±1 (ASTM D 2697)
THINNER CODE	K- Solv 1500
THINNING RATE	%5-8
VOC CONTENT	356 g/L (ASTM D 3960)
SPREADING RATE	7-8 sqm per liter when applied as single coat (100 microns DFT)
SURFACE DRY TIME	3 hours @20 °C
THROUGH DRY	18 hours @20 °C
COMPLETELY CURED	9 days @20 °C
HARDENER TYPE - COMP. MIXING RATIO	K-Cure 22000 , 5,65:1 on Volume
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0,0219 - 0,023"
PRESSURE INFO	150-180 bars
RECOMMENDED WET THICKNESS	200 microns
DRY FILM THICKNESS	120 microns
MINIMUM RECOATING INTERVAL	18 hours @20 °C
MAXIMUM RECOATING INTERVAL	Not limited
MAXIMUM RECOATING INTERVAL(IMMERSION)	Not limited
POT LIFE	5 hours @20 °C
SHELF LIFE	2 years for Component A and 2 year for Component B from the date of manufacture, as long as stored at proper conditions and unopened

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501-1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.
REPAIRS	Corroded areas should be blast cleaned to Sa2 ^{1/2} or SSPC SP10. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com



KARDEN UNIMARINE

PRODUCT CODE: KBK 020112

GENERAL PURPOSE MARINE PRIMER-SURFACE TOLERANT



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS

17 Component A + 3L Component B in steel pails

STORAGE CONDITIONS

Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

HEALTH

Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.

SAFETY

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 24.09.2018



KARTALLAR BOYA KIMYA

"Kuruyun Estetik"

KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI

Address : Koslucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE

Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com