

KARDEN METACOAT

PRODUCT CODE: KBK 020118
 ABRASION RESISTANT PRIMER

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Abrasion resistant pure epoxy primer
DESCRIPTION, AREAS OF USE	A two component, polyamine cured aluminium pigmented anticorrosive high performance primer for use on critical marine industry surfaces usch as offshore platforms, underwater hulls, superstructure exteriors, decks, cargo and balast tanks. Direct application on mechanically prepared surfaces or properly cleaned bare steel surfaces is possible.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 - 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) - +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Bronze, Aluminium
APPEARANCE	Semi Matt (ASTM D 523)
SPECIFIC GRAVITY	1,30±05 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	%60±2 (ASTM D 2697)
THINNER CODE	K- Solv 1200
THINNING RATE	Not Recommended
VOC CONTENT	300 g/L (ASTM D 3960)
SPREADING RATE	7 sqm per liter when applied as single coat (100 microns DFT)
SURFACE DRY TIME	3 hours @20 °C
THROUGH DRY	6 hours @20 °C
COMPLETELY CURED	9 days @20 °C
HARDENER TYPE - COMP. MIXING RATIO	K-Cure 20000 - 2,57:1 on Volume
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0.019" - 0.025"
PRESSURE INFO	150-200 bars
RECOMMENDED WET THICKNESS	170 microns
DRY FILM THICKNESS	100 microns
MINIMUM RECOATING INTERVAL	8 hours @20 °C
MAXIMUM RECOATING INERVAL	15 days @20 °C
MAXIMUM RECOATING INERVAL(IMMERSION)	10 days @20 °C for Karden Epotie, Karden Unimarine, Karden Masterguard
POT LIFE	3 hours @20 °C
SHELF LIFE	2 years for Component A and 2 year for Component B from the date of manufacture, as long as stored at proper conditions and unopened

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501-1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.
REPAIRS	Corroded areas should be blast cleaned to Sa2 ^{1/2} or SSPC SPI0. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
 Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com



KARDEN METACOAT

PRODUCT CODE: KBK 020118
ABRASION RESISTANT PRIMER



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS

14,4 Component A + 5,6L Component B in steel pails

STORAGE CONDITIONS

Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

HEALTH

Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.

SAFETY

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 24.09.2018



KARTALLAR BOYA KIMYA

"Kuruyun Estetik"

KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI

Address : Koslucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE

Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com