

KARDEN MASTICOAT

PRODUCT CODE: KBK 020119 HEAVY DUTY EPOXY PAINT



1. DESCRIPTION OF PRODUCT AND THE PRODUCER		
GENERIC TYPE	Self priming, phenalkamine epoxy	
DESCRIPTION, AREAS OF USE	A two component, phenalkamine cured high performance paint with excellent resistance to fresh and saltwater exposure. Outstanding surface and moisture tolerance, low temperature cure ability and very fast cure properties make this product an ideal all seasons solution for heavy duty marine coating applications. Direct aplication on mechanically prepared surfaces or properly cleaned bare steel surfaces is possible. Could be taken fresh and saltwater service after 60 minutes of curing at 25°C.	
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE	
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68	
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93	

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS		
COLOUR(S) / TEXTURE	Gray, Pale Brown	
APPEARANCE	Semi Matt (ASTM D 523)	
SPECIFIC GRAVITY	1,90±05 g/cm³ (ASTM D 1475)	
SOLID BY VOLUME	80±1 (ASTM D 2697)	
THINNER CODE	K- Salv 1600	
THINNING RATE	%8-12	
VOC CONTENT	175 g/L (ASTM D 3960)	
SPREADING RATE	6,2 sqm per liter when applied as single coat (125 microns DFT)	
SURFACE DRY TIME	2 hours @20 ℃	
THROUGH DRY	8 hours @20 °C	
COMPLETELY CURED	7 days @ZO °C	
HARDENER TYPE - COMP. MIXING RATIO	K-Cure 23000 - 4:1 on Volume	
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush	
NOZZLE INFO	0,017" - 0.021"	
PRESSURE INFO	150-200 bars	
RECOMMENDED WET THICKNESS	190 microns	
DRY FILM THICKNESS	150 microns	
MINIMUM RECOATING INTERVAL	3 hours @20 °C	
MAXIMUM RECOATING INERVAL	8 days @20 °C	
MINIMUM CURE TIME FOR IMMERSION	1 hour	
POT LIFE	1,5 hour @20 °C	
SHELF LIFE	2 years for Component A and 2 year for Component B from the date of manufacture, as long as stored at proper conditions and unopenned	

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION		
NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501-1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.	
REPAIRS	Corroded areas should be blast cleaned to $Sa2^{1/2}$ or SSPC SPIO. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.	
SURFACE SALT LIMITS	35µg/sqm	

DATE OF ISSUE : 24.09.2018





KARDEN MASTICOAT

PRODUCT CODE: KBK 02019 HEAVY DUTY EPOXY PAINT



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3° C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40° C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15° C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	16 Component A + 4L Component B in steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety
	regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 24.09.2018

