

KARDEN PRIMER

PRODUCT CODE: KBK 02011
MARINE PRIMER

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Zinc phosphate primer
DESCRIPTION, AREAS OF USE	One pack, alkyd resin based rust preventive primer. Containing well balanced pigment blend against corrosive conditions. A ready mixed and easy to use marine primer for wooden or steel surfaces. Specially developed for inside areas of superstructures.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 - 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) - +90 224 442 82 9 or KBK COATINGS : +90 262 641 49 67 (08:30-18:00 /TR)

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Oxide Red, RedBrown, Grey
APPEARANCE	Flat (ASTM D 523)
SPECIFIC GRAVITY	1.35±0.05 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	%50±2 (ASTM D 2697)
THINNER CODE	K- Solv100
THINNING RATE	%5-8
VOC CONTENT	415 g/L (ASTM D 3960)
SPREADING RATE	12sqm per liter when applied as single coat (40 microns DFT)
SURFACE DRY TIME	2-4 hours @20 °C
THROUGH DRY	8-10 hours @20 °C
COMPLETELY CURED	3 days @20 °C
HARDENER TYPE - RATIOS	N/A
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0.017" - 0.019"
PRESSURE INFO	150-180 bars
RECOMMENDED WET THICKNESS	80 microns
DRY FILM THICKNESS	40 microns
MINIMUM RECOATING INTERVAL	8 hours @20 °C
MAXIMUM RECOATING INTERVAL	Extended @20 °C
POT LIFE	N/A
SHELF LIFE	2 years from the date of manufacture if stored at proper conditions and unopened

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Steel surfaces should be properly primed by this product soon after completion of SA2 blasting. Surface must be clean, dry and free from any contaminants.
REPAIRS	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.
SURFACE SALT LIMITS	35µg/sqm
WOODEN SURFACES	Clean and dry surface. Surface contamination is to be removed by detergents and fresh water cleaning.

DATE OF ISSUE : 21.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com



KARDEN PRIMER

PRODUCT CODE: KBK 02011
MARINE PRIMER



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS

20L steel pails

STORAGE CONDITIONS

Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

HEALTH

Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.

SAFETY

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 21.09.2018



KARTALLAR BOYA KIMYA

"koruyucu Estetik"

KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com