

KARDEN ACRYLA HB

PRODUCT CODE: KBK 020211
MARINE TOPCOAT

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Acrylic topcoat paint
DESCRIPTION, AREAS OF USE	One pack, quick drying high build topcoat paint based on acrylic resin. A ready mixed and easy to use general purpose marine paint to be used as primer, intermediate coat or topcoat. The most suiting KBK Marine product for fast and economical maintenance needs.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 - 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) - +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	KBK Marine Color Card
APPEARANCE	Flat (ASTM D 523)
SPECIFIC GRAVITY	1,20±0,02 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	%42±1 (ASTM D 2697)
THINNER CODE	K- Solv1000
THINNING RATE	%5-10
VOC CONTENT	512 g/L (ASTM D 3960)
SPREADING RATE	4-4,5 sqm per liter when applied as single coat (100 microns DFT)
SURFACE DRY TIME	45 minutes @20 °C
THROUGH DRY	1,5-2 hours @20 °C
COMPLETELY CURED	3 days @20 °C
HARDENER TYPE - RATIOS	N/A
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0,017" - 0,021"
PRESSURE INFO	160-180 bars
RECOMMENDED WET THICKNESS	250 microns
DRY FILM THICKNESS	100 microns
MINIMUM RECOATING INTERVAL	4 hours @20 °C for K-Acryl IK and Karden Acryl HB
MAXIMUM RECOATING INTERVAL	No limitation
PDT LIFE	N/A
SHELF LIFE	3 years from the date of manufacture if stored at proper conditions and unopened

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Steel surfaces should be properly primed by proper KBK Marine Primers or Intermediate Coats soon after completion of SA2 blasting. Surface must be clean, dry and free from any contaminants.
REPAIRS	Corroded areas should be power tool cleaned to ISO-Sa3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com

KARDEN ACRYL HB

PRODUCT CODE: KBK 020211
MARINE TOPCOAT



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS

20L steel pails

STORAGE CONDITIONS

Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

HEALTH

Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.

SAFETY

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 24.09.2018



KARTALLAR BOYA KIMYA

"Kuruyun Estetik"

KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI

Address : Koslucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE

Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com