

KARDEN AQUATOP

PRODUCT CODE: KBK 020223
WATERBORNE MARINE TOPCOAT

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Water based topcoat
DESCRIPTION, AREAS OF USE	High performance, water-based topcoat paint that combines fast drying and good performance. Used at interior steel surfaces of superstructures to prevent long time disturbing odor of solvent based paints.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 - 18:00) Tel: 0262 641 49 67 Fax: 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) - +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	KBK Marine Colours
APPEARANCE	Matt, Semi Matt or Glossy (ASTM D 523)
SPECIFIC GRAVITY	1,10±05 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	40±1 (ASTM D 2697)
THINNER CODE	Demineralized water
THINNING RATE	%3-5
VOC CONTENT	80 g/L (ASTM D 3960)
SPREADING RATE	10 sqm per liter when applied as single coat (40 microns DFT)
SURFACE DRY TIME	45 minutes @20 °C
THROUGH DRY	8 hours @20 °C
COMPLETELY CURED	2 days @20 °C
HARDENER TYPE - COMP. MIXING RATIO	N/A
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0.013" - 0.015"
PRESSURE INFO	120-150 bars
RECOMMENDED WET THICKNESS	100 microns
DRY FILM THICKNESS	40 microns
MINIMUM RECOATING INTERVAL	8 hours @20 °C
MAXIMUM RECOATING INTERVAL	Extended
MINIMUM CURE TIME FOR IMMERSION	N/A
POT LIFE	N/A
SHELF LIFE	1 years from the date of manufacture, as long as stored at proper conditions and unopened

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501-1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.
REPAIRS	Corroded areas should be blast cleaned to Sa2 ^{1/2} or SSPC SPI0. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel : +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com



KARDEN AQUATOP
PRODUCT CODE: KBK 020223
WATERBORNE MARINE TOPCOAT



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS	The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80
-------------------------------	---

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	4L or 20L in plastic containers
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER	The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.
-------------------	--

DATE OF ISSUE : 24.09.2018



KARTALLAR BOYA VE KIMYA SANAYİ TİCARET LİMİTED SİRKETİ

Address : Koslucaesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel : +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com