

KARDEN PRIMAFOUL

PRODUCT CODE: KBK 02031 Antifouling system primer

DESCRIPTION OF PRODUCT AND THE PRODUCER

GENERIC TYPE	Anticorrosive, epoxy primer
DESCRIPTION, AREAS OF USE	Two pack epoxy paint that could be dried in short times even at low temperatures down. Resitance to saltwater, oils, corrosion and abrasion are key features.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Grey, Dxide Red
APPEARANCE	Matte (ASTM D 523)
SPECIFIC GRAVITY	1,50±0,05 g/cm³ (ASTM D 1475)
SOLID BY VOLUME	%60±5 (ASTM D 2697)
THINNER CODE	K- Salv 300
THINNING RATE	%4-6
VOC CONTENT	282 _g /L (ASTM D 3960)
SPREADING RATE	5,5-6 sqm per liter when applied as single coat (125 microns DFT)
SURFACE DRY TIME	2 hours @20 °C
THROUGH DRY	8 hours @20 °C
COMPLETELY CURED	7 days @20 °C
HARDENER TYPE - COMP. MIXING RATIO	K-Cure 1000 , 3,5:1 by Volume
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0,019" - 0.023"
PRESSURE INFO	160-200 bars
RECOMMENDED WET THICKNESS	175 microns
DRY FILM THICKNESS	125 microns
MINIMUM RECOATING INTERVAL	4 hours @20 °C for K-Acryl IK , 4 hours @20 °C for Karden Eposea, Karden Epotie and Karden Unimarine and Karden Premium
MAXIMUM RECOATING INERVAL	10 hours @20 °C for K-Acryl 1K , 15 days @20 °C for Karden Premium
MAXIMUM RECOATING INERVAL(IMMERSION)	30 days @20 °C for Karden Epotie and Karden Unimarine
POT LIFE	6 hours @20 °C
SHELF LIFE	2 years for Component A and 2 year for Component B from the date of manufacture, as long as stored at proper conditions and unopenned

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501- 1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.
REPAIRS	Corroded areas should be blast cleaned to $Sa2^{1/2}$ or SSPC SPIO. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018





KARDEN PRIMAFOUL

PRODUCT CODE: KBK 02031 ANTIFOULING SYSTEM PRIMER

ENVIRONMENT CONDITIONS	The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured
	in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film

SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	15.75L Component A + 4.25L Component B in steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER	The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the
	substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever
	arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the
	product without notice

DATE OF ISSUE: 24.09.2018

