

KARPOX EPOGLASS

PRODUCT CODE: KBK 030117
GLASSFLAKE EPOXY COATING

**1. DESCRIPTION OF PRODUCT AND THE PRODUCER**

GENERIC TYPE	Epoxy-amine + glassflake coating
DESCRIPTION, AREAS OF USE	Three pack, self priming, chemically resistant epoxy – cycloaliphatic amine plus glassflake reinforced versatile coating for marine and industrial uses. Thanks to excellent strength in the dried paint film, extreme impact, abrasion and mechanical resistance properties are obtained. Can also be modified by suitable fillers to serve as an anti-skid coating. Continuous dry heat resistance upto 150°C.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Grey, Oxide Red
APPEARANCE	Egshell (ASTM D 523)
SPECIFIC GRAVITY	1,80±0,05 g/cm ³ (ASTM D 1475)
SOLID BY VOLUME	%78±1 (ASTM D 2697)
THINNER CODE	K- Solv 1200
THINNING RATE	%10 for spray application
VOC CONTENT	238 g/L (ASTM D 3960) (when thinned %10 with K-Solv 1200)
SPREADING RATE	3,5 sqm per liter when applied as single coat (200 microns DFT)
SURFACE DRY TIME	4 hours @20 °C
THROUGH DRY	16 hours @20 °C
COMPLETELY CURED	7 days @20 °C
HARDENER TYPE – COMP. MIXING RATIO	K-Cure 27000 , 1:1 on Volume
METHOD OF APPLICATION	Airless Spray, HVLP Spray, brush. Roller application is not recommended
NOZZLE INFO	0,025" – 0,035"
PRESSURE INFO	150-180 bars
RECOMMENDED WET THICKNESS	260 microns
DRY FILM THICKNESS	200 microns
MINIMUM RECOATING INTERVAL	6 hours @20 °C for same material
MAXIMUM RECOATING INTERVAL	30 days @20 °C for same material
MAXIMUM RECOATING INTERVAL(IMMERSION)	30 days @20 °C for same material
POT LIFE	3 hours @20 °C
SHELF LIFE	3 years for Component A and 18 months for Component B from the date of manufacture, as long as stored at proper conditions and unopened 5 years for Glassflake additive.

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Oil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 ^{1/2} as per ISO 8501-1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to the final application.
REPAIRS	Corroded areas should be blast cleaned to Sa2 ^{1/2} or SSPC SP10. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to the overcoating.
SURFACE SALT LIMITS	35µg/sqm

DATE OF ISSUE : 24.09.2018

**KARTALLAR BOYA VE KIMYA SANAYI TICARET LIMITED SIRKETI**

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel : +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com



KARPOX EPOGLASS

PRODUCT CODE: KBK 030117
GLASSFLAKE EPOXY COATING



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 10°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80. Should only be applied on completely dry surfaces where the ambient temperature is at least 10°C.

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS

4L Component A + 4L Component B + 0.65L Glassflake additive

STORAGE CONDITIONS

Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be separated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

HEALTH

Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.

SAFETY

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 24.09.2018



KARTALLAR BOYA VE KIMYA SANAYİ TİCARET LİMİTED SİRKETİ

Address : Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400- Gebze/ Kocaeli /TURKIYE
Tel: +90 262 641 49 67 E-mail : info@kartallarboya.com Website : www.kartallarboya.com