

KARESTER PRIMER

PRODUCT CODE: KBK 030119 EPOXY ESTER PRIMER



1. DESCRIPTION OF PRODUCT AND THE PRODUCER GENERIC TYPE IK Epoxy Ester Primer DESCRIPTION, AREAS OF USE One pack, rust preventive primer containing well balanced corrosion prevention pigments blend against light to medium degree general industrial corrosive conditions. A ready mixed and easy to apply primer for steel and ferrous metal surfaces. PRODUCER INFORMATION Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE PRODUCT HOTLINE Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax: 0262 641 49 68 EMERGENCY LINE Uludag University Poison Research Center (7/24) – +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS		
COLOUR(S) / TEXTURE	Oxide Red, Grey, Black	
APPEARANCE	Flat (ASTM D 523)	
SPECIFIC GRAVITY	1,35±0,05 g/cm³ (ASTM D 1475)	
SOLID BY VOLUME	%45±1 (ASTM D 2697)	
THINNER CODE	K- Solv 600	
THINNING RATE	%5-10	
VOC CONTENT	520 g/L (ASTM D 3960)	
SPREADING RATE	10 sqm per liter when applied as single coat (45 microns DFT)	
SURFACE DRY TIME	1 hour @20 °C	
TACK FREE DRY	5-6 hours @20 °C	
THROUGH DRY	48 hours @20 °C	
HARDENER TYPE - RATIOS	N/A	
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush	
NOZZLE INFO	HVLP 1,4 mm	
PRESSURE INFO	HVLP 4 bars	
RECOMMENDED WET THICKNESS	100 microns	
DRY FILM THICKNESS	45 microns	
MINIMUM RECOATING INTERVAL	6 hours @20 °C	
MAXIMUM RECOATING INERVAL	15 days @20 °C	
POT LIFE	N/A	
SHELF LIFE	I year from the date of manufacture if stored at proper conditions and unopenned	

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION	
NEW APPLICATION	Steel surfaces should be properly primed by this product soon after completion of SA2 blasting. Surface must be clean, dry and free from any contaminants.
REPAIRS	Corroded areas should be power tool cleaned to ISD-St3 or blast cleaned to ISD-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

DATE OF ISSUE: 16.04.2020





KARESTER PRIMER

PRODUCT CODE: KBK 030119 EPOXY ESTER PRIMER



3 SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUE)	

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	4L Steel Gallons, 20 L steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 16.04.2020

