TECHNICAL DATA SHEET

KARAPID PRIMER PRODUCT CODE: KBK 03012 INDUSTRIAL QUICK DRY PRIMER



1. DESCRIPTION OF PRODUCT AND THE PRODUCER

| GENERIC TYPE | Rapid dry anticorrosive primer |
|---------------------------|---|
| DESCRIPTION, AREAS OF USE | One pack, time saving, rust preventive primer containing well balanced corrosion prevention pigments blend against light to medium degree general industrial corrosive conditions. A ready mixed and easy to apply primer for steel and ferrous metal surfaces. |
| PRODUCER INFORMATION | Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE |
| PRODUCT HOTLINE | Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68 |
| EMERGENCY LINE | Uludag University Poison Research Center (7/24) – +90 224 442 82 93 |

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

| COLOUR(S) / TEXTURE | Oxide Red, Grey |
|----------------------------|---|
| APPEARANCE | Flat (ASTM D 523) |
| SPECIFIC GRAVITY | 1,50±0,05 g/cm³ (ASTM D 1475) |
| SOLID BY VOLUME | %56±1 (ASTM D 2697) |
| THINNER CODE | K- Salv 200 |
| THINNING RATE | %5-12 |
| VOC CONTENT | 255 g/L (ASTM D 3960) |
| SPREADING RATE | 11 sqm per liter when applied as single coat (45 microns DFT) |
| SURFACE DRY TIME | l hour @20 °C |
| THROUGH DRY | 6 hours @20 °C |
| COMPLETELY CURED | 3 days @20 °C |
| HARDENER TYPE - RATIOS | N/A |
| METHOD OF APPLICATION | Airless Spray, HVLP Spray, lint free roller, brush |
| NOZZLE INFO | 0,017" – 0.019" |
| PRESSURE INFO | 150-180 bars |
| RECOMMENDED WET THICKNESS | 80 microns |
| DRY FILM THICKNESS | 45 microns |
| MINIMUM RECOATING INTERVAL | 8 hours @20 °C |
| MAXIMUM RECOATING INERVAL | 15 days @20 °C |
| POT LIFE | N/A |
| SHELF LIFE | 2 years from the date of manufacture if stored at proper conditions and unopenned |

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

| NEW APPLICATION | Steel surfaces should be properly primed by this product soon after completion of SA2 blasting. Surface must be clean, dry and free from any contaminants. |
|-----------------|--|
| REPAIRS | Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating. |

DATE OF ISSUE : 21.09.2018

(KK)



KARAPID PRIMER PRODUCT CODE: KBK 03012 INDUSTRIAL QUICK DRY PRIMER



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS 5 Kg Steel Gallons, 25 Kg steel pails STORAGE CONDITIONS Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

| GENERAL RULES | Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators. |
|---------------|---|
| HEALTH | Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask. |
| SAFETY | This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted. |

6. DISCLAIMER

DISCLAIMER The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE : 21.09.2018

