KAROLEO GALVANIC

PRODUCT CODE: KBK 030313 Aluminium Glaze Paint



DESCRIPTION OF PRODUCT AND THE PRODUCER

GENERIC TYPE	Aluminium glaze paint
DESCRIPTION, AREAS OF USE	One pack glaze paint based on oleoresins. Permanent heat resistance upto 200°C. Protects comperatively hot surfaces serving at industrial
	machines, pipelines, installations and equipments.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi
	Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400
	Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93

2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLDUR(S) / TEXTURE Aluminium APPEARANCE Shiny SPECIFIC GRAVITY D.90±0.02 g/cm³ (ASTM D 1475) SOLID BY VOLUME %38±1 (ASTM D 2697) THINNER CODE No thinning required THINNING RATE N/A VOC CONTENT 509 g/L (ASTM D 3960) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush NOZZLE INFO 0,015" - 0.017"
SPECIFIC GRAVITY 0.90±0,02 g/cm³ (ASTM D 1475) SOLID BY VOLUME %38±1 (ASTM D 2697) THINNER CODE No thinning required THINNING RATE N/A VOC CONTENT 509 g/L (ASTM D 3960) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour 20 °C THROUGH DRY 3-4 hours 20 °C COMPLETELY CURED 5 days 20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
SOLID BY VOLUME 9/38±1 (ASTM D 2697) THINNER CODE No thinning required THINNING RATE N/A VOC CONTENT 5D9 g/L (ASTM D 396D) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
THINNER CODE No thinning required THINNING RATE N/A VOC CONTENT SOP g/L (ASTM D 3960) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
THINNING RATE N/A VOC CONTENT 509 g/L (ASTM D 3960) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
VOC CONTENT 509 g/L (ASTM D 3960) SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
SPREADING RATE 15 sqm per liter when applied as single coat (24 microns DFT) SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
SURFACE DRY TIME 1 hour @20 °C THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
THROUGH DRY 3-4 hours @20 °C COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
COMPLETELY CURED 5 days @20 °C HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
HARDENER TYPE - RATIOS N/A METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
METHOD OF APPLICATION Airless Spray, HVLP Spray, lint free roller, brush
NDZZLE INFD 0,015" – 0.017"
PRESSURE INFO 100 bars
RECOMMENDED WET THICKNESS 65 microns
DRY FILM THICKNESS 24 microns
MINIMUM RECOATING INTERVAL 8 hours @20 °C
MAXIMUM RECOATING INERVAL 3 days @20 °C
POT LIFE N/A
SHELF LIFE 3 years from the date of manufacture if stored at proper conditions and unopenned

3. SURFACE PREPARATION 8 ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Steel surfaces should be properly primed by Karden Octupus soon after completion of SA2 blasting. Surface must be clean, dry and free from any
	contaminants.
REPAIRS	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose
	paint, salt, grease and other contaminants prior to overcoating.

DATE OF ISSUE: 21.09.2018





KAROLEO GALVANIC

PRODUCT CODE: KBK 030313 ALUMINIUM GLAZE PAINT



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3° C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40° C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15° C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	15 Kg steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 21.09.2018

