KARPOX SLIPRESIST

PRODUCT CODE: KBK 030315 Antislip epoxy coating



DESCRIPTION OF PRODUCT AND THE PRODUCER

GENERIC TYPE	Epoxy polyamide antislip coating
DESCRIPTION, AREAS OF USE	Two pack, high build epoxy - polyamide coating for industrial or residential floors where anti-slip properties are required. Carefuly selected agregate mixture prevents setling and guarantee a long term usability. Excellent self priming, abrasion and corrosion resistance.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93

. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	Grey, Oxide Red
APPEARANCE	Egshell (ASTM D 523)
SPECIFIC GRAVITY	1,70±0,05 g/cm³ (ASTM D 1475)
SOLID BY VOLUME	%70±1 (ASTM D 2697)
THINNER CODE	K- Salv 1200
THINNING RATE	%3-5
VOC CONTENT	260 g/L (ASTM D 3960) (when thinned %8 with K-Salv 1200)
SPREADING RATE	5 sqm per liter when applied as single coat (140 microns DFT)
SURFACE DRY TIME	2 hours @20 °C
THROUGH DRY	8 hours @20 °C
COMPLETELY CURED	7 days @20 °C
HARDENER TYPE - COMP. MIXING RATIO	K-Cure 1000 , 6:1 on Weight
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0,017" - 0.023"
PRESSURE INFO	200-220 bars
RECOMMENDED WET THICKNESS	200 microns
DRY FILM THICKNESS	140 microns
MINIMUM RECOATING INTERVAL	6 hours @20 °C for same material
MAXIMUM RECOATING INERVAL	180 days @20 °C for same material
MAXIMUM RECOATING INERVAL(IMMERSION)	30 days @20 °C for same material
POT LIFE	2 hours @2 0 °C
SHELF LIFE	2 years for Component A and 2 years for Component B from the date of manufacture, as long as stored at proper conditions and unopenned

3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Dil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to SaZ ^{1/2} as per ISO 8501-
	1:2007) If a suitable temporary protecting primer was applied, loose debris and any type of contamination should be cleaned thoroughly prior to
	the final application.
REPAIRS	Corroded areas should be blast cleaned to Sa $2^{1/2}$ or SSPC SP10. Existing systems should be dry and free from loose paint, salt, grease and other
	contaminants prior to the overcoating.

DATE OF ISSUE : 24.09.2018





KARPOX SLIPRESIST

PRODUCT CODE: KBK 030315 ANTISLIP EPOXY COATING



3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3° C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40° C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 10° C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80. Should only be applied on completely dry surfaces where the ambient temperature is at least 10° C.

4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	24 Kg Part A + 4 Kg Part B in steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

6. DISCLAIMER

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 24.09.2018

