# KARPOLY PYRAMIDAL

PRODUCT CODE: KBK 03035 POLYURETHANE TOPCOAT PAINT



## DESCRIPTION OF PRODUCT AND THE PRODUCER

GENERIC TYPE	2K Urethane - alkyd enamel
DESCRIPTION, AREAS OF USE	Two pack, aromatic isocyanate cured, glossy urethane alkyd topcoat paint. Has fair color retention and UV resistance. This product is suitable to be used on properly primed steel surfaces of machineries, industrial vehicles and equipments, casted parts, exteriors of petroleum storing and transportation tanks, exteriors of water storage tanks, agricultural equipments and various constructional projects.
PRODUCER INFORMATION	Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400 Gebze / KOCAELI / TURKIYE
PRODUCT HOTLINE	Monday-Saturday (08:30 – 18:00) Tel: 0262 641 49 67 Fax : 0262 641 49 68
EMERGENCY LINE	Uludag University Poison Research Center (7/24) – +90 224 442 82 93

## 2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

COLOUR(S) / TEXTURE	RAL K7 Colors
APPEARANCE	Glossy (ASTM D 523)
SPECIFIC GRAVITY	1,2 O±O,10 g/cm³ (ASTM D 1475)
SOLID BY VOLUME	%50±1 (ASTM D 2697)
THINNER CODE	K- Salv 400
THINNING RATE	%5-8
VOC CONTENT	436 g/L (ASTM D 3960)
SPREADING RATE	10 sqm per liter when applied as single coat (50 microns DFT)
SURFACE DRY TIME	2-2,5 hours @20 °C
THROUGH DRY	7-8 hours @20 °C
COMPLETELY CURED	7 days @20 °C
HARDENER TYPE - RATIOS	K-Cure 3000 , <b>4:1 on Weight</b>
METHOD OF APPLICATION	Airless Spray, HVLP Spray, lint free roller, brush
NOZZLE INFO	0,013"-0,017"
PRESSURE INFO	150-160 bars
RECOMMENDED WET THICKNESS	100 microns
DRY FILM THICKNESS	50 microns
MINIMUM RECOATING INTERVAL	6 hours @20 °C
MAXIMUM RECOATING INERVAL	10 days @2 0 °C
POT LIFE	<b>5 hours</b> @20 °C
SHELF LIFE	3 years for Component A and 1 year for Component B from the date of manufacture, as long as stored at proper conditions and unopenned

## 3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

NEW APPLICATION	Dil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to Sa2 <sup>1/7</sup> as per ISO 8501-
	1:2007) followed by application of a suitable protective primer. Loose debris and any type of other contaminations should be cleaned thoroughly
	prior to the final application. Please consult KBK for coatings system recommendations for each area and purpose.
REPAIRS	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose
	paint, salt, grease and other contaminants prior to overcoating.

DATE OF ISSUE : 24.09.2018





# KARPOLY PYRAMIDAL

PRODUCT CODE: KBK 03035
POLYURETHANE TOPCOAT PAINT



## 3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

#### ENVIRONMENT CONDITIONS

The temperature of the surface should be at least 3°C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is 40°C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 15°C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

## 4. PACKING & STORAGE CONDITIONS

PACKING DETAILS	16 Kg Part A + 4 Kg Part B in steel pails
STORAGE CONDITIONS	Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the
	manufacturing fields to eliminate the risks of fire.

## 5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

GENERAL RULES	Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety
	regulations should be followed. This product is intended for use by professional applicators.
HEALTH	Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask.
SAFETY	This product contains flammable materials and should be kent away from sparks and onen flames. Smoking in the area should not be permitted

### 6. DISCLAIMER

### DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 24.09.2018

