# KARPOX DUALITY

PRODUCT CODE: KBK 03037 EPOXY SELF PRIMED PAINT



# DESCRIPTION OF PRODUCT AND THE PRODUCER

| GENERIC TYPE              | Epoxy topcoat self primed paint  |
|---------------------------|--|
| DESCRIPTION, AREAS OF USE | Two pack epoxy-polyamide based, seld primed topcoat paint for steel surfaces. Used at light to medium duty industrial steel construction       |
| DESCRIPTION, AREAS OF USE | projects. Formulated to provide anticorrosive and esthetic properties by application of a single layer. A time saving product for highly dense |
|                           |  |
|                           | industrial working conditions. Not recommended for direct UV contact.  |
| PRODUCER INFORMATION      | Kartallar Boya ve Kimya Sanayi Ticaret Limited Sirketi   |
|                           | Kosklucesme Mahallesi, Yeni Bagdat Caddesi, No:136, 41400  |
|                           | Gebze / KOCAELI / TURKIYE  |
| PRODUCT HOTLINE           | Monday-Saturday (08:30 – 18:00) Tel:   0262 641 49 67 Fax : 0262 641 49 68   |
| EMERGENCY LINE            | Uludag University Poison Research Center (7/24) – +90 224 442 82 93  |

# 2. PRODUCT'S TECHNICAL & APPLICATION PARAMETERS

| COLOUR(S) / TEXTURE                  | RAL K7 Colors  |
|--------------------------------------|--|
| APPEARANCE                           | Glossy (ASTM D 523)  |
| SPECIFIC GRAVITY                     | 1,35±0,05 g/cm³ (ASTM D 1475)  |
| SOLID BY VOLUME                      | %57±3 (ASTM D 2697)  |
| THINNER CODE                         | K- Salv 300  |
| THINNING RATE                        | %4-10  |
| VOC CONTENT                          | 387 <sub>g</sub> /L (ASTM D 3960)  |
| SPREADING RATE                       | 10 sqm per liter when applied as single coat (60 microns DFT)  |
| SURFACE DRY TIME                     | 1 hour @20 °C  |
| THROUGH DRY                          | 12 hours @20 °C  |
| COMPLETELY CURED                     | 7 days @20 °C  |
| HARDENER TYPE - COMP. MIXING RATIO   | K-Cure 1000 , <b>5:1 on Weight</b>   |
| METHOD OF APPLICATION                | Airless Spray, HVLP Spray, lint free roller, brush   |
| NOZZLE INFO                          | 0,017" - 0.021"  |
| PRESSURE INFO                        | 180-220 bars   |
| RECOMMENDED WET THICKNESS            | 100 microns  |
| DRY FILM THICKNESS                   | 55 microns   |
| MINIMUM RECOATING INTERVAL           | <b>4 hours</b> @20 ℃   |
| MAXIMUM RECOATING INERVAL            | 10 days @2 0 °C  |
| MAXIMUM RECOATING INERVAL(IMMERSION) | Not immersed   |
| POT LIFE                             | <b>6 hours</b> @20 °C  |
| SHELF LIFE                           | 3 years from the date of manufacture if stored at proper conditions and unopenned ( Component A and Component B) |

## 3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION

| NEW APPLICATION | Dil and grease should be removed by solvent cleaning according to SSPC-SPI. Steel surfaces should be abrasive blasted to $Sa2^{1/2}$ as per ISO 85DI-       |
|-----------------|---|
|                 | 1:2007) followed by application of a suitable protective primer. Loose debris and any type of other contaminations should be cleaned thoroughly             |
|                 | prior to the final application. Please consult KBK for coatings system recommendations for each area and purpose.   |
| REPAIRS         | Corroded areas should be blast cleaned to Sa2 <sup>1/2</sup> or SSPC SPIO. Existing systems should be dry and free from loose paint, salt, grease and other |
|                 | contaminants prior to the overcoating.  |

DATE OF ISSUE: 24.09.2018





# KARPOX DUALITY

PRODUCT CODE: KBK 03037 EPOXY SELF PRIMED PAINT



## 3. SURFACE PREPARATION & ENVIRONMENTAL CONDITIONS DURING APPLICATION (CONTINUED)

#### ENVIRONMENT CONDITIONS

The temperature of the surface should be at least  $3^{\circ}$ C higher than the DewPoint of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. The maximum recommended surface temperature is  $40^{\circ}$ C. In extreme cases, it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least  $15^{\circ}$ C. Otherwise extra solvent may be needed to obtain a proper application viscosity. Relative humidity must not be over %80

# 4. PACKING & STORAGE CONDITIONS

| PACKING DETAILS    | 5 Kg Part A + 1 Kg Part B - 20 Kg Part A + 4 Kg Part B   |
|--------------------|--|
| STORAGE CONDITIONS | Storing areas should be dry and well ventilated where the temperature is always between 5-30°C. These areas should be seperated from the |
|                    | manufacturing fields to eliminate the risks of fire.   |

## 5. ENVIRONMENTAL RESPONSIBILITY, HEALTH & SAFETY

| GENERAL RULES | Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.  |
|---------------|---|
| HEALTH        | Avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapors and paint mist by wearing an air mask. |
| SAFETY        | This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.   |

# 6. DISCLAIMER

#### DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

DATE OF ISSUE: 24.09.2018

